

National Masonry Pty Ltd
ABN 94 155 064 136
Riding Boundary Road, Deer Park
PO Box 345, Deer Park, VIC 3023
Ph. 03 9361 6400 Fax. 03 9363 6008
Email: melbourne.sales@nationalmasonry.com.au
www.nationalmasonry.com.au

Last Update: 23/05/2025

TECHNICAL DATA SHEET		
Product Code:	10.01 AG	
Product Description:	90 mm HOLLOW BLOCK A/G STANDARD MIX	
Dimensions:	90 x 190 x 390 mm (W x H x L)	190
Compressive Strength:	Unconfined compressive strength f _{uc} : 10 MPa	
Density:	2100 kg/m ³	
Fire:	Fire Resistance Level (FRL): -/-/60 minutes	
Max Slenderness Ratio for FRL Structural Adequacy:	22.5 for FRL 60 minutes	
Material Thickness for FRL Insulation:	90 mm	
Sound:	Weighted Sound Reduction Index (R _w): less than 43	
R Value (Bare Block)	0.30	
Water Absorption:	7.7% by mass	
Salt Attack Resistance:	General Purpose	
Weight:	11.1 kg	
No. per pallet:	149	
No. per m²:	12.5	
No. per Tonne:	86	

Fire Resistance Levels as per Section 6, AS 3700
Manufactured in accordance to AS/NZS 4455
Dimensions Tolerance +/- 2 mm for Length, Width and Height
Quality Assurance AS/NZS ISO 9001

The test results shown have been recorded in laboratory conditions. Results achieved in the field may vary due to differences in construction techniques or material variations.

For detailed specification to meet your precise requirements, expert advice should be obtained from National Masonry.

The physical properties on the Technical data sheet will also apply to the following products:

10.02AG – (Dimensions: 90 x 190 x 290mm) 10.03AG – (Dimensions: 90 x 190 x 190mm)